

CLAIMS:

1. A multi-piece solid golf ball comprising a solid core and a cover of two inner and outer layers surrounding the  
5 core, the outer cover layer having a surface formed with a plurality of dimples, characterized in that

a product of the Shore D hardness of said inner cover layer multiplied by the Shore D hardness of said outer cover layer and a proportion  $V_R$  (%) of the total of the  
10 volumes of dimple spaces each defined below a plane circumscribed by the dimple edge to the overall volume of a phantom sphere given on the assumption that the golf ball surface is free of dimples satisfy any one of the following combinations (1) to (5):

- 15 (1) the product of Shore D hardnesses of inner and outer cover layers: 1,500 to less than 2,000

$V_R$ : 0.8 to 1.1%

- (2) the product of Shore D hardnesses of inner and outer cover layers: 2,000 to less than 2,500

20  $V_R$ : 0.75 to 1.05%

- (3) the product of Shore D hardnesses of inner and outer cover layers: 2,500 to less than 3,000

$V_R$ : 0.7 to 1%

- (4) the product of Shore D hardnesses of inner and outer  
25 cover layers: 3,000 to less than 3,500

$V_R$ : 0.65 to 0.95%

- (5) the product of Shore D hardnesses of inner and outer cover layers: 3,500 to 4,000

$V_R$ : 0.6 to 0.9%,

- 30 and said dimples include at least three types of dimples which are different in at least one of a diameter, a depth, and a value  $V_0$  which is the volume of one dimple space defined below a plane circumscribed by the dimple edge divided by the volume of a cylinder whose bottom is  
35 the plane and whose height is the maximum depth of the dimple from the bottom.

2. The multi-piece solid golf ball of claim 1 wherein the solid core has a distortion of 2.6 to 6.5 mm under an applied load of 100 kg.
- 5 3. The multi-piece solid golf ball of claim 1 or 2 wherein both the hardnesses of the inner and outer cover layers are up to 63 in Shore D hardness.